

**SPECIFICATIONS/INFORMATION**  
**RE: PARTAC® SILICA GOLF SAND "A" #30/50**

Partac Silica Golf Sand "A"  
Heat-Treated #30-50 (Predominantly .3 - .6mm)

Typical Sand Sieve Analysis

U.S. SCREEN SIZE		PERCENT	
#	MM	RETAINED	PASSING
10	2.0		
12	1.68		
14	1.41		
16	1.19		
18	1.0		
20	.84		
25	.71	0	100
30	.59	2.3	97.7
35	.50	33.8	63.9
40	.42	23.3	40.6
45	.35	24.9	15.7
50	.297	11.6	4.1
60	.250		
70	.21		
100	.149		
PAN		4.1	

1/07

*Your "One-Stop" Source for America's Leading Golf Surfaces & Supplies*

**SPECIFICATIONS/INFORMATION**  
**RE: PARTAC® SILICA GOLF SAND “A” #20/40**

Partac Silica Golf Sand “A”  
Heat-Treated #20-40 (Predominantly .4 - .8mm)

Typical Sand Sieve Analysis

U.S. SCREEN SIZE		PERCENT	
#	MM	RETAINED	PASSING
10	2.0		
12	1.68		
14	1.41		
16	1.19		
18	1.0	0	100
20	.84	1.1	98.9
25	.71	15.1	83.6
30	.59	49.6	34.0
35	.50	27.9	6.1
40	.42	3.5	2.6
45	.35	1.7	.9
50	.297	.6	.3
60	.250		
70	.21		
100	.149		
PAN		.3	

1/07

*Your “One-Stop” Source for America’s Leading Golf Surfaces & Supplies*

**SPECIFICATIONS/INFORMATION**  
**RE: PARTAC® SILICA GOLF SAND "A" #16/35**

Partac Silica Golf Sand "A"  
Heat-Treated #16-35 (Predominantly .5 – 1.2mm)

Typical Sand Sieve Analysis

U.S. SCREEN SIZE		PERCENT	
#	MM	RETAINED	PASSING
10	2.0		
12	1.68		
14	1.41	0	100
16	1.19	1.6	98.4
18	1.0	22.8	75.6
20	.84	32.3	43.3
25	.71	28.2	15.1
30	.59	8.8	6.3
35	.50	3.1	3.2
40	.42	1.1	2.1
45	.35	.7	1.5
50	.297	.8	.7
60	.250		
70	.21		
100	.149		
PAN		.7	

1/07

*Your "One-Stop" Source for America's Leading Golf Surfaces & Supplies*